

AE-NT Best Practices

Surface Preparation

Ensure that the surface is thoroughly clean and dry before AE-NT is applied. Milled surfaces should be swept and vacuumed or blown free of debris.

Application

AE-NT should be applied at a rate of .04 to .1 gallons per square yard. The recommended application temperature is 170°F to 180°F for day light application and 190°F to 195°F for night time application. DO NOT EXCEED 210°F. If applied at lower than recommend temperatures results may vary, some tracking could appear. Don't heat the product more than 5 times in the distributor, or contaminate the product with flush fuel as this could also cause some tracking.

Storage

If stored in a heated tank maintain the product temperature at 170°F to 180°F. If the product is stored in an unheated tank, heat the product in the distributor while it is being circulated to 170°F to 180°F.

Equipment

Recommended spray nozzles to be used are Etnyre part # 3353788 V slot tack nozzle.